



North American Headquarters
 7966 NC 56 Hwy Louisburg, NC 27549
 919.497.0010
www.palzivna.com

Certificate of Compliance

Standard for Approval	WSS-M99P32-D6
Product Description	Vizion V2.0 STD (2.0 PCF)

Properties	Result	Standard	UOM	Status
3.4 Weight (Density)	32	as specified on the engineered drawing	kg/m ³	-
3.5.1 Flammability	56	SE/NRB	mm/min	Dev. Req.
3.6.1 Resistance to Mildew	No Mildew	No Mildew	-	Pass
3.6.2.1 Short Term Heat, Humidity, and Cold	Pending	No Objectable Appearance	-	Pending
3.6.2.2 Heat Aging (90°C)	No Objectable Appearance	No Objectable Appearance	-	Pass
3.6.3 Resistance to Test Reagents	No Tackiness/Delam.	No Tackiness/Delam.	-	Pass
3.6.4 Corrosiveness to Steel	Pending	4 (min)	-	Pending
3.7.2 Tear Resistance	2257	Report	N/m	-
3.7.3 Compression Force Deflection	23	70 (max)	%	Pass
3.7.4.1 Constant Deflection Compression Set (Original)	26	50 (max)	%	Pass
3.7.4.2 Steam Autoclave Aging Exposure	N/A*	+/- 40% max from original value	%	N/A
3.7.4.3 Dry Heat Aging Exposure	N/A*	+/- 10% max from original value	%	N/A
3.7.6 Moisture Absorption	<1.5	30 (max)	%	Pass
3.8.1 Thermal Conductivity	0.0375	Report	W/M.°K	-

Date of Compliance:	31-Aug-15
---------------------	-----------

Palziv North America certifies that this product was inspected and tested in accordance with written standards, and that the results are correct at the time of inspection. Due to the nature of the product, results will vary over time.

*Not applicable for x-linked PE foam

Authorized by

Joe Andolsen
 Quality Manager
 Palziv North America