



Industry Compliance Vizion

Palziv North America
7966 NC 56Hwy Louisburg, NC 27549
919-497-0010

Standard for Approval	GM6075M Type III
Product Description	V6.0 STD

Properties	PXL Data	Standard Requirements	UOM	Status
Average Density	96.11	96 - 116	kg/m ³	Pass
Tensile Strength	907.97	550 (min)	kPa	Pass
Elongation (% to break)	286.87	50 (min)	%	Pass
Tear Resistance	5.16	3.5 (min)	kN/m	Pass
Compression Deflection 25%	280.89	155 - 345	kPa	Pass
Compression Set	10.88	25 (max)	%	Pass
Odor	2	3 (max)		Pass
Cold Flexibility				Pass
Flammability GM9070P				Pass

Date of Compliance	8/2/2010	QA Manager	JoAnn Burtness
--------------------	----------	------------	----------------

Data represents typical values tested in accordance with written standards.

*The information above on **Fuzion**[®] or **Vizion**[®] chemically cross-linked polyethylene foam is presented to the best of our knowledge.*

Results are measured by testing according to ASTM standards.