



Industry Compliance Vizion

Palziv North America
7966 NC 56Hwy Louisburg, NC 27549
919-497-0010

| | |
|-----------------------|--------------------|
| Standard for Approval | GMP.PE.056 Type II |
| Product Description | V4.0 STD |

| Properties | PXL Data | Standard Requirements | UOM | Status |
|----------------------------|----------|-----------------------|-------------------|--------|
| Average Density | 64.07 | 57.6 -73 | kg/m ³ | Pass |
| Tensile Strength | 579.16 | 450 (min) | kPa | Pass |
| Elongation (% to break) | 311 | 95 (min) | % | Pass |
| Tear Resistance | 3.15 | 2.5 (min) | kN/m | Pass |
| Compression Deflection 25% | 121.35 | 53 - 115 | kPa | Pass |
| Compression Set | 9.6 | 35 (max) | % | Pass |
| Water absorption | 0.014 | 0.6 (max) | kg/m ² | Pass |
| Dimensional Stability | -0.75 | -12 (max) | % | Pass |

| | | | |
|--------------------|----------|------------|----------------|
| Date of Compliance | 8/2/2010 | QA Manager | JoAnn Burtness |
|--------------------|----------|------------|----------------|

Data represents typical values tested in accordance with written standards.

*The information above on **Fuzion**® or **Vizion**® chemically cross-linked polyethylene foam is presented to the best of our knowledge.*

Results are measured by testing according to ASTM standards.