



North American Headquarters
 7966 NC 56 Hwy Louisburg, NC 27549
 919.497.0010
www.palzivna.com

Certificate of Compliance				
Standard for Approval		GMW15063- Type 10		
PNA Product Description		V4.0 STD		
Specification/Method	Results	Specified Value	Unit	Status
Fogging/VOCs- GMW3235 Method B-Y1-T1*	2	≤ 4	mg	Pass
Flammability (as is)- GMW3232	26.2	< 100	mm/min	Pass (≥ 0.25" thk.)
Flammability (aged)- GMW3232**	28.4	< 100	mm/min	Pass (≥ 0.25" thk.)
Interior Emissions- GMW15634***	1275	VOC ≤ 600	µg/g	Dev. Req. ****
Interior Emissions- GMW15634***	822	SVOC ≤ 1000	µg/g	Pass
Resistance to Odor Wet Condition (Code A)- GMW3205*****	9.0	≥ 6	-	Pass
Resistance to Odor Dry Condition (Code B)- GMW3205*****	8.5	≥ 6	-	Pass
Mildew- GMW3259	N/A	No Mildew	-	N/A
Thickness- ISO 1923	12.0	Per Engineering Drawing	mm	-
Dimensional Stability- ISO 2796, 90C for 24h.	-1.8	Per Engineering Drawing	%	-
Density- ISO 845	66.8	70 +/- 10	kg/m ³	Pass
Compression Load Deflection 10% Deformation- ISO 844	155	> 25	kPa	Pass
Compression Load Deflection 25% Deformation- ISO 844	171	For Documentation	kPa	-
Compression Load Deflection 50%- ISO 844	245	For Documentation	kPa	-
Tensile Strength- ISO 1798	117	For Documentation	kPa	-
Elongation at Break- ISO 1798	277	For Documentation	%	-
Comp Set 50%, 1/2hr- ISO 1856- B	8.6	For Documentation	%	-
Comp Set 50%, 24hr- ISO 1856- B	2.9	For Documentation	%	-
Date of Compliance:	31-Aug-17			

Palziv North America certifies that this product was inspected and tested in accordance with written standards, and that the results are correct at the time of inspection. Due to the nature of the product, results will vary over time.

* Tested by Reliable Analysis report 1101397R-1676

** Tested by QAI Laboratories report RJ3605-1

*** Tested by FILK report 142726

**** Deviation approved by GM

Joseph R. Andolsen

Joe Andolsen
 Testing Manager
 Palziv North America