



North American Headquarters
 7966 NC 56 Hwy Louisburg, NC 27549
 919.497.0010
www.palzivna.com

Certificate of Compliance

Standard for Approval		GM6075M Type 1		
PNA Product Description		V2.0 STD		
Properties/Test Method	Results	Specified Value	Unit	Status
Density- ASTM D3575, Suffix W	32 (nominal)	28.8-43.2	kg/m ³	Pass
Tensile Strength- ASTM D3575, Suffix T	423	140 (min)	kPa	Pass
Elongation - ASTM D3575, Suffix T	289	30 (min)	%	Pass
Tear Resistance- ASTM D3575, Suffix G	2.47	1.05 (min)	kN/m	Pass
Compression Set- ASTM D3575, Suffix B	24	25 (max)	%	Pass
Thermal Stability- ASTM D3575, Suffix S	-1.4	+/- 5 (max)	%	Pass
Odor- SAE J1351	3/2 (wet/dry) ¹	3 (max)	-	Pass
Compression Deflection- ASTM D3575, Suffix D	48	40 - 103	kPa	Pass
Compression Creep- ASTM D3575, Suffix BB 17.2 kPa for 168 hours	2.7	10 (max)	%	Pass

Date of Compliance:	9-Jan-18
---------------------	----------

Palziv North America certifies that this product was inspected and tested in accordance with written standards, and that the results are correct at the time of inspection. Due to the nature of the product, results will vary over time.

1. Results are for V2.0 SEV. V2.0 STD expected to have similar results.

Authorized by

Joe Andolsen
 Testing Manager
 Palziv North America