



## Preliminary Data Sheet

Vizion 3.0 lb/ft<sup>3</sup> SEV

48 kg/m<sup>3</sup>

Effective Date: 1/5/2016

PHYSICAL PROPERTIES		TEST METHOD	IMPERIAL UNITS	VALUES	METRIC UNITS	VALUES
Density - Nominal		ASTM D3575 - Suffix W	lb/ft <sup>3</sup>	3.0	kg/m <sup>3</sup>	48
Tensile Strength		ASTM D3575 - Suffix T	PSI	66.0	kPa	455
Tear strength		ASTM D3575 - Suffix G	lbf/in	14.6	N/mm	2.56
Elongation at Break		ASTM D3575 - Suffix T	%	377	%	377
Shore Hardness		ASTM D2240	00	53	00	53
Compression Deflection	25%	ASTM D3575 - Suffix D	PSI	7.9	kPa	54.5
	50%			16.9		117.0
Working Temperature Range			°F	-76 / 176	°C	-60 / 80
Water Absorption, 7 days		DIN 53428	% Vol (max)	1	% Vol (max)	1
Flammability, >1/4"		FMVSS302	4"/min	PASS	100mm/min	PASS
Thermal Stability, 24hrs at 158°F (70°C)		ASTM D3575 - Suffix S	%	2	%	2

VIZION is a closed cell chemically crosslinked polyethylene foam in bun form.  
SDS sheets available upon request.

Data represents typical values based on preliminary production runs and should be considered as a guideline only.

Imperial data is converted from the metric results measured by testing according to ASTM standards.

The information above on VIZION chemically crosslinked polyethylene foam is presented to the best of our knowledge.